

Save energy with window films!

Tensile strength 33600 psi 232 N/mm²	Break strength 134 lbs/inch 23 N/mm		Puncture strength 103 lbs 458 N	
	Single Pane	Dual pane	Dual pane low-e	Triple pane low-e
Total Solar Energy Rejected	60%	46%	38%	45%
Visible Light Transmitted	35%	32%	32%	29%
Visible Light Reflected Exterior	25%	27%	27%	31%
Visible Light Reflected Interior	18%	15%	15%	16%
Total Solar Energy Reflected	27%	27%	27%	27%
Total Solar Energy Absorbed	46%	48%	48%	51%
Total Solar Energy Transmitted	27%	25%	25%	22%
SHGC	0,40	0,54	0,62	0,55
UV Rejection	99%	99%	99%	99%
U-Value	6,08	2,77	1,49	1,19
Emissivity	0,84	0,84	0,84	0,84
Compatibility	Compatible	Compatible	Conditionally compatible	Not compatible



K&R Trading Co. Ltd. | H-1195 Budapest, Hofherr A. u. 3/a | www.skyfol.com | info@skyfol.com | SkyFol is a registered trademark